



Rolling mill products

Circles, Shapes and Squares



CIRLCLES AND SQUARES

Thickness in mm	Standard size in mm	Dimension on request	Hardness	On request	Percentage
0,15-0,29	da 35 mm a 600 mm	yes	soft	½ soft - hard	800/°°-925/°°-940/°°-999/°°
0,30-0,99	da 35 mm a 600 mm	yes	soft	½ soft - hard	800/°°-925/°°-940/°°-999/°°
1,00-2,00	da 35 mm a 600 mm	yes	soft	½ soft - hard	800/°°-925/°°-940/°°-999/°°

All circles are produced to meet the requirements for spinning and pressing.
Width steps are in increments of 5 mm.

SHAPES

Thickness in mm	Standard size in mm	Dimension on request	Hardness	On request	Percentage
da 0,25 a 5,00		yes	soft	½ soft - hard	800/°°-925/°°-940/°°-999/°°

We are able to cut shapes to meet customers supplied data.

Our values considering Vickers hardness

	Silver Alloy 800/°°	Silver Alloy 925/°°	Silver Alloy 930/°°	Silver Alloy 999/°°
soft	85 hv	69 hv	67 hv	38-45 hv
½ soft - hard	120 hv	105 hv	102 hv	65-70 hv
hard	150 hv	145 hv	140 hv	100 hv