

Brazing Alloys

Silver brazing alloys flux coated



Silver brazing alloys flux coated

Code	Composition %					Melting point °C	Standard coat/colour
	Ag	Cu	Zn	Cd	Other		
200 R	20,0	44,0	36,0		Yes	690 - 810	standard / white
210 R	21,0	36,0	27,0	16,0		605 - 730	standard / white
250 R	25,0	40,0	33,0		Sn	680 - 760	standard / white
734 R	34,0	36,0	27,5		Sn	630 - 730	standard / white
400 R	40,0	30,0	28,0		Sn	640 - 700	standard / white
745 R	45,0	27,0	25,5		Sn	640 - 660	standard / white

Our technical staff will be pleased to assist customers with any queries regarding material and costs.

All information and facts with reference to the products specified are accurate and reliable to our knowledge but are supplied without any guarantee or responsibility. PMP Firenze srl not being acquainted with the eventual final use or application of the above said information, declines any responsibility for losses or damage to persons or objects that may be derived from an inappropriate use of the information provided. In addition, the technical information contained within the schedules are susceptible to eventual changes at any given moment and without prior warning on the part of PMP Firenze srl.